

**(19) World Intellectual Property
Organization
International Bureau**



(43) International Publication Date
19 August 2004 (19.08.2004)


PCT

(10) International Publication Number
WO 2004/070066 A1

- (51) International Patent Classification⁷: C22B 1/08, 34/32
- (21) International Application Number:
PCT/CA2004/000165
- (22) International Filing Date: 6 February 2004 (06.02.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2,418,546 6 February 2003 (06.02.2003) CA
60/445,437 7 February 2003 (07.02.2003) US
- (71) Applicant (for all designated States except US):
RESSOURCES MINIERES PRO-OR INC. [CA/CA];
400 rue St-Jacques, Suite 200, Montreal, Quebec H2Y 1S1
(CA).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): BERGERON,
Mario [CA/CA]; 1253 De Fenouillet, Cap Rouge, Quebec
G1Y 2Y6 (CA). RICHER-LAFLECHE, Marc [CA/CA];
- 1303 rue De Chambly, Sainte-Foy, Quebec G1W 3Y8
(CA).
- (74) Agents: DUBUC, J. et al.; Goudreau Gage Dubuc, Stock
Exchange Tower, 800 Place Victoria, Suite 3400, P.O. Box
242, Montreal, Quebec, H4Z 1E9 (CA).
- (81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MY, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.
- (84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: A METHOD FOR INCREASING THE CHROME TO IRON RATIO OF CHROMITES PRODUCTS



(57) **Abstract:** A method for increasing the chrome to iron ratio of a chromite product selected from the group consisting of ore and ore concentrate comprising the steps of mixing the chromite product with at least one salt so as to produce a mixture, whereby the concentration of salt in the mixture is selected to induce the selective chlorination of iron; and chlorinating the mixture in the presence of CO at a temperature sufficient to induce the formation of a thin film of a melt around the chromite product and at a temperature able to promote the selective chlorination of iron, whereby an iron impoverished chromite product is yielded having an increased chromite to iron ratio as compared to that of the chromite product.

BEST AVAILABLE COPY

WO 2004/070066 A1